

MONOTEX 20

Clear Anti-Skid Additive

TECHNICAL
BULLETIN



MADE IN U.S.A.

PRODUCT DESCRIPTION:

MONOTEX 20 is a micronized polypropylenes that creates a skid resistant coating for concrete, wood, metal or fiberglass when mixed with paints, stains or film forming sealers. The fine rounded shape of **MONOTEX 20** is less abrasive when compared to silica texturing agents and will not change the color, sheen, performance or properties of the coating.

ADVANTAGES

- Easy to disperse into any type of paint and coating
- The particle size is uniform to produce an even textured surface in coatings.
- Provides optimum abrasion resistance when mixed with floor coatings
- Easy to walk on with bare feet. The rounded shape is less abrasive and provides a smoother feel when compared to other types of texturing agents.
- Mix with one gallon of Water Based or Oil Based Paints, Solid Stains or Sealers.
- Meets American with Disabilities Act (ADA)
- It Meets and Exceeds ASTM C1028-07 (Coefficient of Friction Std): 0.60-0.80

WHERE TO USE:

- Driveways
- Walkways
- Garages
- Decks
- Porches
- Patios
- Ramps
- Stairs

APPLICATION:

The level of addition depends on the degree of textured desired.

STEP 1:

Apply one coat of **MONOBOND** primer.

STEP 2:

• **For one component coatings**, add **MONOTEX 20** using a high speed mixer for 2-3 minutes until it is evenly dispersed. Stir frequently during use to prevent settling.

• **For two component coatings**, add the **MONOTEX 20** to the Part A component (do not add to the catalyst/activator Part B) using a high speed mixer for 2-3 minutes until it is evenly dispersed. Stir frequently during use to prevent settling.

• Apply a small test patch to ensure the proper performance and appearance.

• **MONOTEX 20** should be added to the base coat (the coat right before the top coat) and not the final/top/primer coat of an application.

RECOMMENDED USE:

The below recommended **MONOTEX 20** mixing ratios are approximations based on how much is mixed with Monopole Coatings.

100% Solids Coatings (Monochem 21, Permashield 2000)

Lighter Texture: ¼ pound (½ pint) per 96 Oz Kit or 1 pound per 3-Gallon Kit.

Moderate to Heavy Texture: ½ pound (1 pint) per 96 Oz Kit or 2 pounds per 3-Gallon Kit.

20-60% Solids Coatings (Permashield 200, Monochem 200)

Lighter Texture: ⅛-¼ pound (¼- ½ pint) per gallon.

Moderate to Heavy Texture: ½ pound (1 pint) per gallon.

Adding too much **MONOTEX 20** may lead to a milky appearance.

PACKAGING:

ITEM NO. M20-16OZ: **MONOTEX 20 (16 OZ KIT)**

½ pound

COVERAGE RATES:

*The spread rates listed below vary based on the surface texture and the quantity of **MONOTEX** added to the coating.*

• **PERMASHIELD 200:** 150-175 square feet per gallon

• **MONOCHEM 200:** 150-175 square feet per gallon

• **PERMASHIELD 2000:** 175-200 square feet per gallon

• **MONOCHEM 21:** 175-200 square feet per gallon

WARNING! IRRITANT, HARMFUL IF SWALLOWED, READ OUR SDS.

WARRANTY INFORMATION: All the recommended products will mirror the performance and soundness of the structure, previous coatings and filling/patching (repair) materials. For an ideal application, we recommend removing the existing coatings. If this is not an option, remove all unsound, loose and/or poorly adhering paint and conduct thorough test patches. Delamination or the failure of the existing/non Monopole coatings is not covered by any performance warranty. MONOPOLE believes that the information in this publication is an accurate description of the typical characteristics and/or uses of the product or products. But it is the end users responsibility to thoroughly test the product in the specific application to determine its performance efficacy and safety. Since use of this product is beyond our control, Monopole, Inc. cannot assume any risk or liability for results obtained when not used according to our specifications and directions. Unless MONOPOLE provides a specific written statement of fitness for a particular use, MONOPOLE'S sole warranty is that the product will meet its current sales specifications. MONOPOLE specifically disclaims any other expressed or implied warranty, including the warranty of merchantability and fitness for use. The exclusive remedy and MONOPOLE's sole liability for breach of warranty is limited to a refund of the purchase price or replacement of product proven to be defective. In no event shall the seller be liable for any loss of profits or other consequential damages. Under no circumstance will MONOPOLE pay labor charges.

DECORATIVE FLOOR ADDITIVES

MONOPOLE INC.
UPDATED MARCH 2018



Chemex Industries, Inc.

3 Chattanooga, Irvine, CA 92620 ▪ Phone: 714-832-8441 ▪ Fax: 714-832-8103